

PFC Corofil Ablative Coating

Installation Instructions

PFC Corofil Ablative Coating is used to reinstate the ablative surface of PFC Corofil Coated panels

If you are unsure about any details within this method statement, please email tech@pfc-corofil.com

General

- PFC Corofil Ablative Coating should only be applied when the ambient temperature is between 0°C and +30°C
- Ensure the PFC Corofil Coated Panel has been installed correctly (see TDPANE & MSPANE for details).
- PFC Corofil Ablative Coating should be brush or spray applied to a nominal 2.5mm Wet Film Thickness (WFT).
- Apply PFC Corofil Ablative Coating to all joints, cracks, fissures and bare fibres on the PFC Corofil Coated Panel.

Health & Safety Instructions

Please refer to SDCOAT

Other Information

Please ensure the product(s) described within this method statement have been tested in, and are suitable for your application.

Doc Reference				MSCOAT			
PB	SE	CB	CI	AB			
This Copy				Review Date			
April 2018				April 2020			